## APPENDIX

## SUMMARY TABLES OF GRADE DESCRIPTIONS

(Informative)

The summary of the descriptions given in Tables 1 and 2 is not exhaustive and does not take the place of the requirements set out in this Standard. Reference should be made to the appropriate Sections of Australian Grading Standard for a complete description of the grades.

TABLE 1
SUMMARY OF NON-PERMISSIBLE FEATURES

Surface		SELECT GRADE (SEL)		MEDIUM FEATURE GRADE—Standard (MF)	Э	HIGH FEATURE GRADE (HF)
Any	•	Enclosed termite galleries	٠	Enclosed termite galleries	•	Enclosed termite galleries
surface	•	Heart shakes	•	Heart shakes	•	Heart shakes
	•	Shakes	٠	Shakes	•	Shakes
	•	Cross-fractures, cross-shakes	•	Cross-fractures, cross-shakes	•	Cross-fractures, cross-shakes
	•	Splits	•	Splits	•	Splits
	•	End splits	•	End splits	•	End splits
	٠	Decay, primary rot	•	Decay, primary rot	•	Decay, primary rot
	•	Lyctid-susceptible sapwood	•	Lyctid-susceptible sapwood	•	Lyctid-susceptible sapwood
Any	٠	Loose knots	•	Loose knots	•	Want and wane
exposed surface	•	Loose gum veins	•	Want and wane	•	Mechanical damage
	•	Gum pockets, latex pockets	•	Mechanical damage	•	Stain other than natural
	•	Overgrowth of injury	•	Stain other than natural		discolouration and discolouration of sapwood
	•	Knot checks		discolouration and discolouration of sapwood		due to preservatives
	٠	Want and wane		due to preservatives	•	Sticker marks
	•	Mechanical damage	•	Sticker marks		
	•	Stain other than natural discolouration and				
		discolouration of sapwood due to preservatives				
	•	Sticker marks				

TABLE 2
SUMMARY OF PERMISSIBLE FEATURES IN HARDWOOD PRODUCTS

Feature	SELECT GRADE (SEL)	MEDIUM FEATURE GRADE— Standard (MF)	HIGH FEATURE GRADE (HF)	Concealed surface grade— for SEL, MF and HF grades
	On exposed surfaces			On concealed surfaces
Tight knots and any associated voids; individually or in aggregate in any 1 m of board length	Not exceeding 15 mm or 1/4 of the surface on which it occurs	Not exceeding 40 mm or 1/3 of the surface on which it occurs	Not exceeding 50 mm or 3/8 of the surface on which it occurs	<ul> <li>Not exceeding 1/3 of the surface on which it occurs; and</li> <li>Not within 3 mm of any exposed surface</li> </ul>
Loose Knots	Not permitted	Not permitted	As for holes	As for holes
Holes (borer, non-enclose	ed termite galleries and other)			
(a) Length	Not exceeding the lesser of 15 mm or 1/4 of the surface on which it occurs	Not exceeding the lesser of 40 mm or 1/3 of the surface on which it occurs	Not exceeding the lesser of 50 mm or 3/8 of the surface on which it occurs	_
(b) Width	Exceeding 2 mm— not permitted     Not exceeding 2 mm—     Boards of width up to and including 50 mm—     2 holes per 100 mm     4 holes per 900 mm     Boards of width over 50 mm up to and including 100 mm—     5 holes per 100 mm     10 holes per 900 mm     Boards of width over 100 mm—     8 holes per 100 mm     16 holes per 900 mm	Exceeding 3 mm—not permitted     Not exceeding 3 mm—     Boards of width up to and including 50 mm—     8 holes per 100 mm     12 holes per 900 mm     Boards of width over 50 mm up to and including 100 mm—     16 holes per 100 mm     24 holes per 900 mm     Boards of width over 100 mm—     24 holes per 100 mm     36 holes per 900 mm	Exceeding 10 mm, not permitted. Exceeding 3 mm and not exceeding 10 mm—not more than 3 in any 1 metre length of board  Not exceeding 3 mm—  Boards of width up to and including 50 mm—  8 holes per 100 mm  12 holes per 900 mm  Boards of width over 50 mm up to and including 100 mm—  16 holes per 100 mm  24 holes per 900 mm  Boards of width over 100 mm—  24 holes per 100 mm  24 holes per 100 mm	<ul> <li>Exceeding 10 mm—         <ul> <li>loss of cross-section at any position in the length of the board not exceeding 1/5 of the cross-section; and</li> <li>Not within 3 mm of any exposed surface</li> </ul> </li> <li>Exceeding 3 mm and not exceeding 10 mm—loss of cross section at any position in the length of the board not exceedin 1/5 of the cross-section</li> <li>Not exceeding 3 mm—unlimited</li> </ul>
Slope of grain	Not exceeding 1 in 8	• Not exceeding 1 in 8	• 36 holes per 900 mm • Not exceeding 1 in 8	Not exceeding 1 in 8

(continued)

 TABLE 2 (continued)

Feature	SELECT GRADE (SEL)	MEDIUM FEATURE GRADE Standard (MF)	HIGH FEATURE GRADE (HF)	Concealed surface grade— for SEL, MF and HF grades
	On exposed surfaces			On concealed surfaces
Tight gum veins	Not exceeding— o surface width measured across the feature, 2 mm o individual length, 250 mm o aggregate length, 1/2 the length of the piece	Quartersawn—surface width measured across the feature, not exceeding 5 mm Backsawn— cextent across face unlimited surface width measured across the feature not exceeding 60 mm individual length not exceeding 1 m depth not exceeding 2 mm	Quartersawn—surface width measured across feature, not exceeding 5 mm Backsawn— o extent across face unlimited o depth not exceeding 2 mm	Quartersawn—surface width measured across feature, not exceeding 5 mm     Backsawn—     o extent across face unlimited o depth not exceeding 5 mm
Loose gum veins	Not permitted	<ul> <li>Not one surface to another</li> <li>Not intersecting an end</li> <li>Surface width measured across the feature—not exceeding 3 mm</li> <li>Agg, length not exceeding 1/5 of the length of the piece</li> </ul>	<ul> <li>Not one surface to another</li> <li>Not intersecting an end</li> <li>Surface width measured across the feature, not exceeding 3 mm</li> <li>Agg. length not exceeding 1/5 of the length of the piece</li> </ul>	<ul> <li>Not one surface to another</li> <li>Not intersecting an end</li> <li>Surface width measured across the feature, not exceeding 3 mm</li> <li>Agg, length not exceeding 1/5 of the length of the piece</li> </ul>
Gum pockets, latex pockets and overgrowth of injury	Not permitted	Not one surface to another Surface width measured across the feature, not exceeding 10 mm Length not exceeding 50 mm Backsawn—depth not exceeding 2 mm	Not one surface to another Surface width measured across the feature, not exceeding 15 mm Length not exceeding 75 mm Backsawn—depth not exceeding 2 mm	Not one surface to another     Length not exceeding 300 mm     Quartersawn—surface width measured across the feature, not exceeding 30 mm     Backsawn—depth not exceeding 5 mm
Knot checks	Not permitted	Width not exceeding 2 mm	Width not exceeding 3 mm	Width not exceeding 5 mm
Checks other than internal (Note 1)	Width not exceeding 1 mm     Individual length not exceeding 250 mm	Width not exceeding 2 mm     Individual length not exceeding 250 mm	Width not exceeding 2 mm	Width not exceeding 3 mm
Stain (Note 2) Natural discolouration	• Slight (Note 3)	Unlimited	Unlimited	Unlimited
Other discolouration including sticker marks	Not permitted	Not permitted	Not permitted	Unlimited
Black speck (Note 2)	Slight (Note 3)	Unlimited	Unlimited	Unlimited

 TABLE 2 (continued)

Feature	SELECT GRADE (SEL)	MEDIUM FEATURE GRADE— Standard (MF)	HIGH FEATURE GRADE (HF)	Concealed surface grade—for SEL, MF and HF grades
		On exposed surfaces		On concealed surfaces
Non-Lyctid-susceptible sapwood (which includes appropriately treated sapwood)	• Unlimited	Unlimited	Unlimited	Unlimited
Burls	• Unlimited	Unlimited	Unlimited	Unlimited
Hobnails	No significant colour variation— unlimited	No significant colour variation— unlimited	Unlimited	• Unlimited
	Significant colour variation, width measured at right angles to board—not exceeding 15 mm	Significant colour variation, width measured at right angles to board— not exceeding 40 mm		
Want, wane and mechanical damage	Not permitted	Not permitted	Not permitted	Width not exceeding 1/3 of the width of the surface on which it occurs
				• Aggregate length not exceeding 300 mm
				• Not within 3 mm of any exposed surface

## NOTES:

- Timber products purporting to comply with this Standard are graded visually. Some features such as internal checks cannot always be seen by the grader; therefore, it is considered inappropriate to include internal checks as part of the grading rules. After further profiling of the timber (often by another party), the previously unseen internal checks may be revealed on the surface of the newly profiled product. When this occurs, they should be assessed as 'checks other than internal' because they are now on the surface. Internal checks are not considered acceptable in some products and care should be exercised during drying to limit their occurrence.
- When it is intended to apply a paint or similar pigmented finish to a product, then discolouration, stain or black speck need not be limited when agreed between the purchaser and supplier.
- The interpretation of the word slight will depend on the species being graded. The word slight has been used, even though it is subjective, because of the difficulty in describing what is a small or trifling amount of a feature, which may create a visual impact on the product. The visual impact of colour variation within a board will depend on a number of factors. A 'slight' feature is considered not to have a large impact on the overall appearance. For example, a floor with considerable color variation between heartwood and sapwood may tolerate greater discolouration in some boards without affecting the overall appearance of the floor. In other instances where the timber is predominantly of one colour (particularly of a lighter tone), the contrast created by a small amount of discolouration within a board will heavily impact on the overall appearance and should not be considered slight.